

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
4 July 2002 (04.07.2002)

PCT

(10) International Publication Number
WO 02/051705 A2

- (51) International Patent Classification⁷: **B65B 55/08**, 55/19
- (74) Agents: **QUATT, Mark, B.** et al.; Cryovac, Inc., P.O. Box 464, 100 Rogers Bridge Rd., Duncan, SC 29334 (US).
- (21) International Application Number: **PCT/US01/47870**
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (22) International Filing Date:
11 December 2001 (11.12.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- (30) Priority Data:
60/258,030 22 December 2000 (22.12.2000) US
09/860,389 18 May 2001 (18.05.2001) US
- (71) Applicant (*for all designated States except US*): **CRY-
OVAC, INC.** [US/US]; P.O. Box 464, 100 Rogers Bridge
Rd., Duncan, SC 29334 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): **COTTERMAN,
Ronald, L.** [US/US]; 524 Spaulding Lake Drive,
Greenville, SC 29615 (US). **SPEER, Drew, V.** [US/US];
204 English Oak Road, Simpsonville, SC 29681 (US).
- Published:**
— *without international search report and to be republished
upon receipt of that report*
- For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*



WO 02/051705 A2

(54) Title: METHOD OF STERILIZING AND INITIATING A SCAVENGING REACTION IN AN ARTICLE

(57) **Abstract:** A method includes providing an article including an oxygen scavenger; forming the article into a container; placing an oxygen sensitive product into the container; and exposing the container to actinic radiation at a dosage effective to sterilize the container, and trigger the oxygen scavenger in the article. Alternative methods are also disclosed. A package includes a container, the container including an activated oxygen scavenger; wherein the container is sterilized; and wherein an oxygen sensitive product is disposed in the container.

METHOD OF STERILIZING AND INITIATING A SCAVENGING
REACTION IN AN ARTICLE

Field Of The Invention

5 The invention generally relates to a method of initiating an oxygen scavenging reaction in an article during a gamma sterilization process typical of those used for medical products.

Background Of The Invention

10 A number of sterilization processes are used in the health care industry, including gamma radiation, ethylene oxide treatment, and steam (thermal) treatment. In the food industry, retort processes, gamma radiation, electron beam radiation and microwave radiation are used.

For the packaging of intravenous solutions and the like, sterilization of the primary packaging material is critical.

15 Many medical products such as intravenous solutions are oxygen sensitive and therefore it is desirable to use oxygen scavengers in their packaging. It would be desirable to conveniently and simply supply a single packaging material which can be sterilized by gamma radiation for medical applications, and which includes an oxygen scavenger which
20 is triggered or activated by the same gamma ray sterilization that is used to sterilize the packaging material. This would then avoid the need for a separate triggering step, or for a separate insertion of an oxygen scavenger in a resulting package, or for a master pack and separate individual packets.

25 Incorporating an oxygen scavenger into the packaging material itself achieves a more uniform scavenging effect throughout the package. This may be especially important where there is restricted air circulation inside the package. In addition, such incorporation can provide a means of intercepting and scavenging oxygen as it passes through the walls of the package, thereby maintaining the lowest possible oxygen level throughout the package.

30 Oxygen scavengers suitable for commercial use in articles of the present invention, such as films, are disclosed in U.S. Patent No. 5,350,622, and a method of initiating oxygen scavenging generally is disclosed in U.S. Patent No 5,211,875. According to U.S. Patent No. 5,350,622, oxygen scavengers are made of an ethylenically unsaturated hydrocarbon and transition metal catalyst. The ethylenically unsaturated hydrocarbon may be either
35 substituted or unsubstituted. As defined herein, an unsubstituted ethylenically unsaturated

hydrocarbon is any compound that possesses at least one aliphatic carbon-carbon double bond and comprises 100% by weight carbon and hydrogen. A substituted ethylenically unsaturated hydrocarbon is defined herein as an ethylenically unsaturated hydrocarbon which possesses at least one aliphatic carbon-carbon double bond and comprises about 50% -
5 99% by weight carbon and hydrogen. Preferable substituted or unsubstituted ethylenically unsaturated hydrocarbons are those having two or more ethylenically unsaturated groups per molecule. More preferred is a polymeric compound having three or more ethylenically unsaturated groups and a molecular weight equal to or greater than 1,000 weight average molecular weight.

10 Examples of unsubstituted ethylenically unsaturated hydrocarbons include, but are not limited to, diene polymers such as polyisoprene (e.g. trans-polyisoprene) and copolymers thereof, cis and trans 1,4-polybutadiene, 1,2-polybutadiene, (which is defined as a polybutadiene possessing greater than or equal to 50% 1,2 microstructure), and copolymers thereof, such as styrene-butadiene copolymer. Such hydrocarbons also include
15 polymeric compounds such as polypentenamer, polyoctenamer, and other polymers prepared by cyclic olefin metathesis; diene oligomers such as squalene; and polymers or copolymers with unsaturation derived from dicyclopentadiene, norbornadiene, 5-ethylidene-2-norbornene, 5-vinyl-2-norbornene, 4-vinylcyclohexene, 1,7-octadiene, or other monomers containing more than one carbon-carbon double bond (conjugated or non-conjugated).

20 Examples of substituted ethylenically unsaturated hydrocarbons include, but are not limited to, those with oxygen-containing moieties, such as esters, carboxylic acids, aldehydes, ethers, ketones, alcohols, peroxides, and/or hydroperoxides. Specific examples of such hydrocarbons include, but are not limited to, condensation polymers such as polyester derived from a monomer containing a carbon-carbon double bond, and unsaturated fatty
25 acids such as oleic, ricinoleic, dehydrated ricinoleic, and linoleic acid and derivatives thereof, e.g. esters. Such hydrocarbons also include polymers or copolymers derived from (meth)allyl (meth)acrylates. Suitable oxygen scavenging polymers can be made by transesterification. Such polymers are disclosed in US Patent No. 5,859,145 (Ching et al.) (Chevron Research and Technology Company). The composition used may also comprise
30 a mixture of two or more of the substituted or unsubstituted ethylenically unsaturated hydrocarbons described above. While a weight average molecular weight of 1,000 or more is preferred, an ethylenically unsaturated hydrocarbon having a lower molecular weight is usable, especially if it is blended with a film-forming polymer or blend of polymers.

Ethylenically unsaturated hydrocarbons which are appropriate for forming solid transparent layers at room temperature are preferred for scavenging oxygen in the packaging articles described above. For most applications where transparency is necessary, a layer which allows at least 50% transmission of visible light is preferred.

5 When making transparent oxygen-scavenging layers according to this invention, 1,2-polybutadiene is useful at room temperature. For instance, 1,2-polybutadiene can exhibit transparency, mechanical properties and processing characteristics similar to those of polyethylene. In addition, this polymer is found to retain its transparency and mechanical integrity even after most or all of its oxygen uptake capacity has been consumed, and even
10 when little or no diluent resin is present. Even further, 1,2-polybutadiene exhibits a relatively high oxygen uptake capacity and, once it has begun to scavenge, it exhibits a relatively high scavenging rate as well.

 When oxygen scavenging at low temperatures is desired, 1,4-polybutadiene, and copolymers of styrene with butadiene, and styrene with isoprene are useful. Such compositions are disclosed in U.S. Patent No. 5,310,497 issued to Speer et al. on May 10, 1994.
15 In many cases it may be desirable to blend the aforementioned polymers with a polymer or copolymer of ethylene.

 An additional example of oxygen scavengers which can be used in connection with this invention are disclosed in PCT patent publication WO 99/48963 (Chevron Chemical et al.). These oxygen scavengers include a polymer or oligomer having at least one cyclohexene group or functionality. These oxygen scavengers include a polymer having a polymeric backbone, cyclic olefinic pendent group, and linking group linking the olefinic pendent group to the polymeric backbone.
20

 An oxygen scavenger suitable for use with the invention comprises:
25 (a) a polymer or lower molecular weight material containing substituted cyclohexene functionality according to the following diagram:

 where A may be hydrogen or methyl and either one or two of the B groups is a heteroatom-containing linkage which attaches the cyclohexene ring to the said material, and wherein the remaining B groups are hydrogen or methyl;

30 (b) a transition metal catalyst; and optionally
 (c) a photoinitiator.

The composition may be polymeric in nature or it may be a lower molecular weight material. In either case it may be blended with one or more further polymers or other additives. In the case of low molecular weight materials, the above composition is preferably compounded with a carrier resin before use.

5 When used in forming a packaging article, the oxygen scavenger used in connection with the present invention can include only the above-described polymers and a transition metal catalyst. However, photoinitiators can be added to further facilitate and control the initiation of oxygen scavenging properties. Adding a photoinitiator or a blend of photoinitiators to the oxygen scavenging composition can be preferred, especially where
10 antioxidants have been added to prevent premature oxidation of the composition during processing and storage.

Suitable photoinitiators are known to those skilled in the art. See, e.g., PCT publication WO 97/07161, WO 97/44364, WO 98/51758, and WO 98/51759. Specific examples of suitable photoinitiators include, but are not limited to, benzophenone, and its
15 derivatives, such as methoxybenzophenone, dimethoxybenzophenone, dimethylbenzophenone, diphenoxybenzophenone, allyloxybenzophenone, diallyloxybenzophenone, dodecyloxybenzophenone, dibenzosuberone, 4,4'-bis(4-isopropylphenoxy)benzophenone, 4-morpholinobenzophenone, 4-aminobenzophenone, tribenzoyl triphenylbenzene, tritoluoyl triphenylbenzene, 4,4'-bis(dimethylamino)-benzophe-
20 none, acetophenone and its derivatives, such as, o-methoxy-acetophenone, 4'-methoxy-acetophenone, valerophenone, hexanophenone, α -phenyl-butyrophenone, p-morpholino-propiophenone, benzoin and its derivatives, such as, benzoin methyl ether, benzoin butyl ether, benzoin tetrahydropyranyl ether, 4-o-morpholinodeoxybenzoin, substituted and unsubstituted anthraquinones, α -tetralone, acenaphthenequinone, 9-acetylphenanthrene,
25 2-acetyl-phenanthrene, 10-thioxanthenone, 3-acetyl-phenanthrene, 3-acetylinole, 9-fluorenone, 1-indanone, 1,3,5-triacetylbenzene, thioxanthen-9-one, isopropylthioxanthen-9-one, xanthene-9-one, 7-H-benz[de]anthracen-7-one, 1'-acetonaphthone, 2'-acetonaphthone, acetonaphthone, benz[a]anthracene-7,12-dione, 2,2-dimethoxy-2-phenylacetophenone, α,α -diethoxyacetophenone, α,α -dibutoxyacetophenone, 4-benzoyl-
30 4'-methyl(diphenyl sulfide) and the like. Single oxygen-generating photosensitizers such as Rose Bengal, methylene blue, and tetraphenylporphine as well as polymeric initiators such as poly(ethylene carbon monoxide) and oligo[2-hydroxy-2-methyl-1-[4-(1-methylvinyl)phenyl] propanone] also can be used. However, photoinitiators are preferred because they generally provide faster and more efficient initiation. When actinic radiation

is used, photoinitiators also can provide initiation at longer wavelengths which are less costly to generate and present less harmful side effects than shorter wavelengths.

When a photoinitiator is present, it can enhance and/or facilitate the initiation of oxygen scavenging by the oxygen scavenger upon exposure to radiation. The appropriate amount of photoinitiator depends on the amount and type of cyclic unsaturation present in the polymer, the wavelength and intensity of radiation used, the nature and amount of antioxidants used, and the type of photoinitiator used. The amount of photoinitiator also can depend on how the scavenging composition is used. For instance, if a photoinitiator-containing composition is in a film layer, which underneath another layer is somewhat opaque to the radiation used, more initiator might be needed. However, the amount of photoinitiator used for most applications ranges from about 0.01 to about 10% (by wt.) of the total composition. Oxygen scavenging can be initiated by exposing an article containing the oxygen scavenger to actinic or electron beam radiation, as described below.

Also suitable for use in the present invention is the oxygen scavenger of copending US Patent Application USSN 09/350336, filed July 9, 1999, which discloses a copolymer of ethylene and a strained, cyclic alkylene, preferably cyclopentene; and a transition metal catalyst.

Another oxygen scavenger which can be used in connection with this invention is the oxygen scavenger of US Patent No. 6,214,254 (Gauthier et al.), which discloses ethylene/vinyl aralkyl copolymer and a transition metal catalyst.

As indicated above, the ethylenically unsaturated hydrocarbon is combined with a transition metal catalyst. Suitable metal catalysts are those which can readily interconvert between at least two oxidation states.

Preferably, the catalyst is in the form of a transition metal salt, with the metal selected from the first, second or third transition series of the Periodic Table. Suitable metals include, but are not limited to, manganese II or III, iron II or III, cobalt II or III, nickel II or III, copper I or II, rhodium II, III or IV, and ruthenium II or III. The oxidation state of the metal when introduced is not necessarily that of the active form. The metal is preferably iron, nickel or copper, more preferably manganese and most preferably cobalt. Suitable counterions for the metal include, but are not limited to, chloride, acetate, stearate, palmitate, caprylate, linoleate, tallate, 2-ethylhexanoate, neodecanoate, oleate or naphthenate. Particularly preferable salts include cobalt (II) 2-ethylhexanoate, cobalt stearate, and cobalt (II) neodecanoate. The metal salt may also be an ionomer, in which case a polymeric counterion is employed. Such ionomers are well known in the art.

Any of the above-mentioned oxygen scavengers and transition metal catalyst can be further combined with one or more polymeric diluents, such as thermoplastic polymers which are typically used to form film layers in plastic packaging articles. In the manufacture of certain packaging articles well known thermosets can also be used as the polymeric
5 diluent.

Polymers which can be used as the diluent include, but are not limited to, polyethylene terephthalate (PET), polyethylene, low or very low density polyethylene, ultra-low density polyethylene, linear low density polyethylene, polypropylene, polyvinyl chloride, polystyrene, and ethylene copolymers such as ethylene-vinyl acetate, ethylene-alkyl
10 (meth)acrylates, ethylene-(meth)acrylic acid and ethylene-(meth)acrylic acid ionomers. Blends of different diluents may also be used. However, as indicated above, the selection of the polymeric diluent largely depends on the article to be manufactured and the end use. Such selection factors are well known in the art.

Further additives can also be included in the composition to impart properties desired for the particular article being manufactured. Such additives include, but are not necessarily limited to, fillers, pigments, dyestuffs, antioxidants, stabilizers, processing aids, plasticizers, fire retardants, anti-fog agents, etc.
15

The mixing of the components listed above is preferably accomplished by melt-blending at a temperature in the range of 50°C to 300°C. However, alternatives such as
20 the use of a solvent followed by evaporation may also be employed. The blending may immediately precede the formation of the finished article or preform or precede the formation of a feedstock or masterbatch for later use in the production of finished packaging articles.

Oxygen scavenging structures can sometimes generate reaction byproducts, which
25 can adversely affect the packaged material or raise food regulatory issues. These byproducts can include organic acids, aldehydes, ketones, and the like. This problem can be minimized by the use of polymeric functional barriers.

Polymeric functional barriers for oxygen scavenging applications are disclosed in WO 96/08371 to Ching *et al.* (Chevron Chemical Company), and WO 94/06626 to Balloni *et al.*
30 *et al.* Functional barriers are also disclosed in copending US Patent Application Serial Nos. 08/813752 (Blinka *et al.*) and 09/445645 (Miranda). The materials in these publications and applications collectively include high glass transition temperature (T_g) glassy polymers such as polyethylene terephthalate (PET) and nylon 6 that are preferably further oriented; low T_g polymers and their blends; a polymer derived from a propylene monomer; a polymer

derived from a methyl acrylate monomer; a polymer derived from a butyl acrylate monomer; a polymer derived from a methacrylic acid monomer; polyethylene terephthalate glycol (PETG); amorphous nylon; ionomer; a polymeric blend including a polyterpene; and poly (lactic acid). The functional barrier polymer(s) may further be blended with another polymer
5 to modify the oxygen permeability as required by some applications. The functional barriers can be incorporated into one or more layers of a multilayer film, container, or other article that includes an oxygen scavenging layer.

In certain applications of oxygen scavenging, it is desirable to provide polymeric materials with low oxygen transmission rates, i.e. with high barrier to oxygen. In these
10 cases, it is preferred that the oxygen permeability of the barrier be less than $500 \text{ cm}^3 \text{ O}_2 / \text{m}^2 \cdot \text{day} \cdot \text{atmosphere}$ (tested at 1 mil thick and at 25 °C according to ASTM D3985), preferably less than 100, more preferably less than 50 and most preferably less than 25 $\text{cm}^3 \text{ O}_2 / \text{m}^2 \cdot \text{day} \cdot \text{atmosphere}$ such as less than 10, less than 5, and less than 1 $\text{cm}^3 \text{ O}_2 / \text{m}^2 \cdot \text{day} \cdot \text{atmosphere}$. The exact oxygen permeability optimally required for a given
15 application can readily be determined through experimentation by one skilled in the art. In medical applications, high barrier is often required to protect the quality of the product being packaged over the intended lifetime of the product. Higher oxygen permeability can readily be accomplished by blending the barrier polymer with any polymer that has a substantially higher oxygen permeability. Useful polymers for blending with barrier
20 polymers include but are not limited to polymers and copolymers of alkyl acrylates, especially ethylene/butyl acrylate; ethylene/vinyl acetate copolymers; and the like. In addition to blending, one skilled in the art will recognize that the barrier can be adjusted through the specification of the resin and thickness.

25 Definitions

"Film" herein means a film, laminate, sheet, web, coating, or the like which can be used to package a product.

"Oxygen scavenger" (OS) and the like herein means a composition, article or the like which consumes, depletes or reacts with oxygen from a given environment.

30 "Functional barrier" herein means a polymeric material, which acts as a selective barrier to by-products from the oxygen scavenging reaction, but is not itself a significant barrier to oxygen.

"LLDPE" herein means linear low density polyethylene, which is an ethylene/ α -olefin copolymer.

"EVOH" herein means ethylene/vinyl alcohol copolymer.

"EVA" herein means ethylene/vinyl acetate copolymer.

"Polymer" and the like herein means a homopolymer, but also copolymers thereof, including bispolymers, terpolymers, etc.

5 "Ethylene/alpha-olefin copolymer" and the like herein means such heterogeneous materials as linear low density polyethylene (LLDPE), linear medium density polyethylene (LMDPE) and very low and ultra low density polyethylene (VLDPE and ULDPE); and homogeneous polymers such as metallocene catalyzed polymers such as EXACT (TM) materials supplied by Exxon, and TAFMER (TM) materials supplied by Mitsui Petrochemical
10 Corporation. These materials generally include copolymers of ethylene with one or more comonomers selected from C₄ to C₁₀ alpha-olefins such as butene-1 (i.e., 1-butene), hexene-1, octene-1, etc. in which the molecules of the copolymers comprise long chains with relatively few side chain branches or cross-linked structures. This molecular structure is to be contrasted with conventional low or medium density polyethylenes which are more highly branched than their
15 respective counterparts. Other ethylene/alpha-olefin copolymers, such as the long chain branched homogeneous ethylene/alpha-olefin copolymers available from the Dow Chemical Company, known as AFFINITY (TM) resins, are also included as another type of ethylene alpha-olefin copolymer useful in the present invention. It is further contemplated that single-site catalyzed polyethylenes, known as Versipol™ (DuPont), will be useful in the present invention.

20 "Polyamide" and the like herein means any polymer having amide linkages along the molecular chain, and preferably to synthetic polyamides such as nylons. Furthermore, such term encompasses both polymers comprising repeating units derived from monomers, such as caprolactam, which polymerize to form a polyamide, as well as polymers derived from a diacid and diamine and copolymers of two or more amide monomers, including nylon terpolymers, also
25 referred to generally as "copolyamides" herein.

 "Medical product" and the like herein means any product which is preferably sterilized prior to use in health care, whether for medical, dental, or veterinary applications, such as those used during medical intervention. This is exemplified but not limited to needles, syringes, sutures, wound dressings such as bandages, general wound dressings, non-
30 adherent dressings, burn dressings, surgical tools such as scalpels, gloves, drapes, and other disposal items, solutions, ointments, antibiotics, antiviral agents, blood components such as plasma, drugs, biological agents, intravenous solutions, saline solutions, surgical implants, surgical sutures, stents, catheters, vascular grafts, artificial organs, cannulas, wound care devices, dialysis shunts, wound drain tubes, skin sutures, vascular grafts, im-

plantable meshes, intraocular devices, heart valves, biological graft materials, tape closures and dressings, head coverings, shoe coverings, sterilization wraps, and the like.

“Trigger” and the like herein means that process defined in U.S. Patent No. 5,211,875, whereby oxygen scavenging is initiated (i.e. activated) by exposing an article
5 such as a film to actinic radiation, such as ionizing radiation, such as gamma radiation, having a wavelength of less than about 750 nm at an intensity of at least about 1.6 mW/cm² or an electron beam at a dose of at least 0.2 megarads (MR), wherein after initiation the oxygen scavenging rate of the article is at least about 0.05 cc oxygen per day per gram of oxidizable organic compound for at least two days after oxygen scavenging is
10 initiated. Preferred is a method offering a short “induction period” (the time that elapses, after exposing the oxygen scavenging component to a source of actinic radiation, before initiation of the oxygen scavenging activity begins) so that the oxygen scavenging component can be activated at or immediately prior to use during filling and sealing of a container, made wholly or partly from the article, with an oxygen sensitive material.

15 Thus, “trigger” refers to exposing an article to actinic radiation as described above; “initiation” refers to the point in time at which oxygen scavenging actually begins or is activated; and “induction time” refers to the length of time, if any, between triggering and initiation.

“Sterilize” and the like herein means the effective inactivation or kill of microbes contained in or on a product. The level of inactivation or kill may vary, but it will be in an
20 amount or at a level acceptable by the applicable commercial and/or FDA standards for the intended product.

Summary Of The Invention

25 In one aspect of the invention, a method comprises providing an article comprising an oxygen scavenger; forming the article into a container; placing an oxygen sensitive product into the formed container; and exposing the formed container, with the oxygen sensitive product therein, to actinic radiation at a dosage effective to sterilize the container, and trigger the oxygen scavenger in the article.

30 In a second aspect of the invention, a method comprises providing a container comprising an oxygen scavenger; providing an oxygen sensitive product; placing the oxygen sensitive product into the container; and exposing the container, with the oxygen sensitive product therein, to actinic radiation at a dosage effective to sterilize the container, and trigger the oxygen scavenger in the container.

In a third aspect of the invention, a method comprises providing an article comprising an oxygen scavenger; forming the article into a container; exposing the formed container to actinic radiation at a dosage effective to sterilize the container, and trigger the oxygen scavenger in the article; and placing an oxygen sensitive product into the formed container.

In a fourth aspect of the invention, a method comprises providing an article comprising an oxygen scavenger; providing an oxygen sensitive product; packaging the oxygen sensitive product in a container formed at least in part from the article; and exposing the formed container, with the oxygen sensitive product therein, to actinic radiation at a dosage effective to sterilize the container, and trigger the oxygen scavenger in the article.

In a fifth aspect of the invention, a method comprises providing an article comprising an oxygen scavenger; providing an oxygen sensitive product; exposing the article to actinic radiation at a dosage effective to sterilize the article, and trigger the oxygen scavenger in the article; and packaging the oxygen sensitive product in a container formed at least in part from the article.

In a sixth aspect of the invention, a package comprises a container, the container comprising an activated oxygen scavenger; wherein the container is sterilized, and wherein an oxygen sensitive product is disposed in the container.

In the above-described aspects:

- the article is preferably in form of a film, such as a film comprising a layer comprising an oxygen scavenger; and a layer comprising a polymer having an oxygen transmission rate of less than $500 \text{ cm}^3 / \text{m}^2 \cdot \text{day} \cdot \text{atm}$ (ASTM D 3985-95);
- the oxygen scavenger preferably comprises a material selected from the group consisting of:
 - i) oxidizable organic compound and a transition metal catalyst,
 - ii) ethylenically unsaturated hydrocarbon and a transition metal catalyst,
 - iii) a polymer having a polymeric backbone, cyclic olefinic pendent group, and linking group linking the olefinic pendent group to the polymeric backbone;
 - iv) a copolymer of ethylene and a strained, cyclic alkylene; and
 - v) ethylene/vinyl aralkyl copolymer;
- the article is preferably a pouch, bag, tray, or lidstock;
- the oxygen sensitive product is preferably a medical product such as intravenous solution, or a food product;

- the oxygen sensitive product is packaged in a container formed at least in part from the article, by preferably

- i) placing the oxygen sensitive product in a pouch formed from the film containing the oxygen scavenger;
- 5 ii) wrapping the oxygen sensitive product in a film containing an oxygen scavenger, and sealing the film to form a hermetic package; or
- 10 iii) placing the oxygen sensitive product in a tray, covering the tray with a lidstock, and sealing the lidstock to the tray to form a hermetic package, wherein at least one of the tray and the lidstock comprises an oxygen scavenger.

Detailed Description Of The Invention

The inventor has found that packaging materials can be triggered to scavenge oxygen during a sterilization process typical of those used for health care products (e.g. gamma radiation). One significant advantage is that a packaging structure, especially a high oxygen barrier structure, can be simultaneously sterilized while initiating oxygen scavenging of the oxygen in the interior of a container made in part or entirely from the article, and/or while initiating oxygen scavenging that provides an active barrier to further ingress of oxygen from the exterior of the container. Both of these attributes (sterilizing of the packaging materials and oxygen scavenging) are desirable for product quality, and extended shelf life of oxygen sensitive products. The packaging structure can take the form of a flexible film, laminate, sheet, or web which can be formed into a bag or pouch, or alternatively can take the form of a semi-rigid or rigid tray or container, such as a bottle.

Although the two functions, sterilization and oxygen scavenging, preferably occur simultaneously, those skilled in the art will understand, after a review of the invention disclosed herein, that some amount of time may elapse between the point in time at which sterilization of the packaging material occurs, and the point in time at which oxygen scavenging initiates.

Examples

One example of a conventional packaging structure requiring oxygen and moisture barrier is a multilayer film construction as follows:

(outside of package)	Abuse Resistant Layer	gas barrier layer	Moisture Barrier Layer	Sealant layer	(inside of package)
----------------------	-----------------------	-------------------	------------------------	---------------	---------------------

In accordance with the present invention, an oxygen scavenger can be either added to or combined with the gas barrier layer:

(outside of package)	Abuse Resistant Layer	gas barrier + oxygen scavenger layer	Moisture Barrier Layer	sealant layer	(inside of package)
----------------------	-----------------------	--------------------------------------	------------------------	---------------	---------------------

5 Alternatively, the oxygen scavenger can be added as a separate layer or layers:

(outside of package)	abuse resistant layer	gas barrier layer	moisture barrier layer	oxygen scavenger layer	sealant layer	(inside of package)
----------------------	-----------------------	-------------------	------------------------	------------------------	---------------	---------------------

or

(outside of package)	abuse resistant layer	gas barrier layer	oxygen scavenger layer	moisture barrier layer	sealant layer	(inside of package)
----------------------	-----------------------	-------------------	------------------------	------------------------	---------------	---------------------

10 Other layers can optionally be included as appropriate, such as one or more adhesive layers, as shown by each of the following three examples:

(outside of package)	abuse resistant layer	adhesive layer	gas barrier + oxygen scavenger layer	adhesive layer	moisture barrier layer	sealant layer	(inside of package)
----------------------	-----------------------	----------------	--------------------------------------	----------------	------------------------	---------------	---------------------

or

15

(outside of package)	abuse resistant layer	adhesive layer	gas barrier layer	adhesive Layer	moisture barrier layer	oxygen scavenger layer	sealant layer	(inside of package)
----------------------	-----------------------	----------------	-------------------	----------------	------------------------	------------------------	---------------	---------------------

or

(outside of package)	abuse resistant layer	adhesive layer	gas barrier layer	adhesive Layer	oxygen scavenger layer	moisture barrier layer	sealant layer	(inside of package)
----------------------	-----------------------	----------------	-------------------	----------------	------------------------	------------------------	---------------	---------------------

A functional barrier layer can optionally be included in the packaging structure:

(outside of package)	abuse resistant layer	gas barrier + oxygen scavenger layer	moisture barrier layer	sealant layer	functional barrier	(inside of package)
----------------------	-----------------------	--------------------------------------	------------------------	---------------	--------------------	---------------------

or

5

(outside of package)	abuse resistant layer	gas barrier layer	moisture barrier layer	oxygen scavenger layer	Sealant layer	functional barrier	(inside of package)
----------------------	-----------------------	-------------------	------------------------	------------------------	---------------	--------------------	---------------------

or

(outside of package)	abuse resistant layer	gas barrier layer	oxygen scavenger layer	moisture barrier layer	Sealant layer	functional barrier	(inside of package)
----------------------	-----------------------	-------------------	------------------------	------------------------	---------------	--------------------	---------------------

10

In the above article constructions:

The abuse resistant layer preferably comprises a material such as ethylene/alpha-olefin copolymer, polypropylene, propylene/ethylene copolymer, high density polyethylene, linear low density polyethylene, polyamide, or blends of any of the above;

15 The gas barrier layer preferably comprises a material such as ethylene/vinyl alcohol copolymer (EVOH), polyvinylidene dichloride, vinylidene chloride/ methyl acrylate copolymer, polyamide, polyester; metallized PET, metal foil, and SiOx compounds;

The adhesive layer preferably comprises a material such as an anhydride grafted polymer or copolymer;

20 The moisture barrier layer preferably comprises a material such as propylene polymer or copolymer, high density polyethylene, ethylene/alpha-olefin copolymer, or ethylene-norbornene copolymer;

The sealant layer preferably comprises a material such as ethylene/alpha-olefin copolymer, ethylene/vinyl acetate copolymer, ethylene/(meth)acrylate copolymer, ethylene/(meth)acrylic acid copolymer, and the like;

25 The functional barrier layer preferably comprises a material such as those disclosed herein; and

The oxygen scavenging layer preferably comprises a material such as those disclosed herein.

For maximum product benefit, the sterilization/initiation process should be carried out prior to product packaging, or immediately after product packaging, depending on the product application. For initiation of the oxygen scavenging reaction, the point in the packaging process or use cycle at which the product is sterilized will affect the configuration of the final packaging structure. For example, packaging products that are triggered a week or more prior to use need to have their oxygen scavenging rate tailored so as to avoid prematurely exhausting their scavenging capacity. This can be accomplished through the use of gas barrier layers flanking the oxygen scavenging layer, or by formulating the oxygen scavenging layer to have a pre-determined induction time between triggering and initiation of oxygen scavenging.

Product applications requiring rapid oxygen scavenging would be designed to have oxygen permeable layers between the scavenging layer or layers and the interior (product side) of the package.

Film of the invention can be made by any conventional means, including coextrusion, lamination, extrusion coating, solution coating, or corona bonding, and then optionally oriented. The film can optionally be made heat shrinkable through orientation or tenter-framing if desired, at orientation ratios of 1:2 to 1:9 in either or both of the machine and transverse directions. To further increase the ability to shrink it may be desirable to irradiate some of the layers of the structure prior to adding the layers containing the scavenger. For shrink applications, the film can be made to have a free shrink of at least 10%, more preferably at least 20%, most preferably at least 30%, in either or both directions at 90°C.

Examples

Multilayer films used in the examples were prepared via cast coextrusion. Each of the films had a nine-layer structure and had a total thickness of approximately 7.35 mils.

The materials used in the examples are identified below. All percentages are weight percents unless otherwise indicated. All physical property and compositional values are approximate unless otherwise indicated. In the examples:

"EPC" = Z9540™, a propylene/ethylene copolymer having an ethylene content of about 6 weight percent and a density of about 0.89 g/cc obtained from Fina Oil and Chemical Company.

"SEBS" = KRATON™ G-1652, a styrene-ethylene-butadiene-styrene block copolymer with a specific gravity of about 0.91, obtained from Shell Chemical Company.

"EAO-1" = ENGAGE™ EG 8100, an ethylene-octene copolymer having a density of approximately 0.87 g/cc, a melt index about 1 dg/min and about 24% octene, obtained from the Dow Chemical Company.

5 "SBS" = VECTOR™ 8508D, a styrene-butadiene-styrene block copolymer with a butadiene content of about 75 wt%, obtained from Dexco.

"CO-NDA" = TEN-CEM™ 170, a cobalt neodecanoate compound with about 22.5 wt% cobalt, obtained from OMG Chemicals.

10 "EVA" = LD-318.29™, an ethylene-vinyl acetate copolymer with approximately 9 mol% vinyl acetate, a density of 0.930 and melt index about 2.0, obtained from Exxon Chemical Company.

"EAO-2" = EXACT™ 3128, an ethylene/alpha-olefin copolymer with a melt index approximately 1.2 and a density about 0.900, obtained from Exxon Chemical Company.

15 "APE" = PLEXAR™ 380, an anhydride-modified linear low density polyethylene tie resin with a density of 0.912 and a melt index about 1.5, obtained from Quantum Chemical Company.

"EVOH" = EVAL™ F101A, an ethylene/vinyl alcohol copolymer with approximately 32 mol % ethylene, a density about 1.2 and a melt index about 1.6, obtained from Evalca.

20 "EMA" = BYNEL™ CXA E374, an anhydride modified ethylene/methyl acrylate copolymer having a melt index of about 2.8 and a density of about 0.931, obtained from E.I. DuPont de Nemours.

"CPE" = ECDEL™ 9965, a copolyester ether having a density about 1.13, obtained from Eastman Chemical Company.

Example 1

25 A multilayer film in accordance with the present invention had the following 9-layer structure

	Layer	Gauge	Component
	1	75	80% EPC/20%SEBS
	2	40	50% EAO-1/40%SBS/10%EVA/680ppmCO-NDA
	3	175	100% EAO-2
30	4	40	100% APE
	5	75	100% EVOH
	6	40	100% APE
	7	175	100% EAO-2
	8	40	EMA
35	9	75	CPE

Example 2

In order to determine the effect of gamma irradiation on the film of Example 1, a film sample was treated with gamma irradiation at an average dose of 39 kGy (3.9 megarads).

- 5 This dose was selected to be representative of a level useful for sterilization of packaged medical products.

Example 3

- 10 Samples of non-irradiated (Example 1) and irradiated (example 2) film were tested for oxygen transmission rate as an indication of oxygen scavenging ability. Oxygen transmission values were obtained using a test method described in detail in U.S. Patent 5,583,047 (Blinka et al.). The results of the test on the two samples at two times are shown in Table 1.

15

Table 1
Oxygen Transmission Rate, cc/m²/day

Time (hours post irradiation)	Example 1 (non-irradiated)	Example 2 (irradiated)
20 5	0.58	0.22
53	0.58	0.24

- 25 This example clearly shows that the multilayer films, when treated with a level of gamma irradiation sufficient to sterilize packaged products, effectively triggered the multilayer films to begin scavenging oxygen. The triggered films show a dramatic reduction in overall oxygen permeability by a factor between 2 and 3 for this example. This degree of permeability decrease would be expected to have a significant, positive effect, on extending the shelf life of oxygen-sensitive package contents.

- 30 The articles of the present invention have been described primarily in connection with the packaging of medical products. However, it is to be understood that other applications for the articles are also possible.

WHAT IS CLAIMED IS:

1. A method comprising:
 - a) providing an article comprising an oxygen scavenger;
 - b) forming the article into a container;
 - c) placing an oxygen sensitive product into the formed container; and
 - d) exposing the formed container, with the oxygen sensitive product therein, to actinic radiation at a dosage effective to sterilize the container, and trigger the oxygen scavenger in the article.
2. A method comprising:
 - a) providing a container comprising an oxygen scavenger;
 - b) providing an oxygen sensitive product;
 - c) placing the oxygen sensitive product into the container; and
 - d) exposing the container, with the oxygen sensitive product therein, to actinic radiation at a dosage effective to sterilize the container, and trigger the oxygen scavenger in the container.
3. A method comprising:
 - a) providing an article comprising an oxygen scavenger;
 - b) forming the article into a container;
 - c) exposing the formed container to actinic radiation at a dosage effective to sterilize the container, and trigger the oxygen scavenger in the article; and
 - d) placing an oxygen sensitive product into the formed container.
4. The method of claims 1 or 3 comprising providing an article in form of a film.
5. The method of claims 1 or 3 comprising providing an article in form of a film, wherein the film comprises:
 - a) a layer comprising an oxygen scavenger; and
 - b) a layer comprising a polymer having an oxygen transmission rate of less than $500 \text{ cm}^3/\text{m}^2 \cdot \text{day} \cdot \text{atm}$ (ASTM D 3985-95).

6. The method of claims 1, 2, or 3 wherein the oxygen scavenger comprises a material selected from the group consisting of:
- i) oxidizable organic compound and a transition metal catalyst,
 - ii) ethylenically unsaturated hydrocarbon and a transition metal catalyst,
 - 5 iii) a polymer having a polymeric backbone, cyclic olefinic pendent group, and linking group linking the olefinic pendent group to the polymeric backbone;
 - iv) a copolymer of ethylene and a strained, cyclic alkylene; and
 - v) ethylene/vinyl aralkyl copolymer.
- 10 7. The method of claims 1, 2, or 3 wherein the container is a pouch, bottle, or tray.
8. The method of claims 1, 2, or 3 wherein the oxygen sensitive product is a medical product.
- 15 9. The method of claims 1, 2, or 3 wherein the oxygen sensitive product is intravenous solution.
10. The method of claims 1, 2, or 3 comprising exposing the container to gamma radiation at a dosage of at least 0.2 megarads to sterilize the container, and trigger the oxygen
- 20 scavenger.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
4 July 2002 (04.07.2002)

PCT

(10) International Publication Number
WO 02/051705 A3

(51) International Patent Classification⁷: **B65B 55/08**,
55/19

(21) International Application Number: PCT/US01/47870

(22) International Filing Date:
11 December 2001 (11.12.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/258,030 22 December 2000 (22.12.2000) US
09/860,389 18 May 2001 (18.05.2001) US

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

(88) Date of publication of the international search report:
6 March 2003

(71) Applicant (*for all designated States except US*): **CRY-OVAC, INC.** [US/US]; P.O. Box 464, 100 Rogers Bridge Rd., Duncan, SC 29334 (US).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **COTTERMAN, Ronald, L.** [US/US]; 524 Spaulding Lake Drive, Greenville, SC 29615 (US). **SPEER, Drew, V.** [US/US]; 204 English Oak Road, Simpsonville, SC 29681 (US).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(74) Agents: **QUATT, Mark, B.** et al.; Cryovac, Inc., P.O. Box 464, 100 Rogers Bridge Rd., Duncan, SC 29334 (US).



WO 02/051705 A3

(54) Title: METHOD OF STERILIZING AND INITIATING A SCAVENGING REACTION IN A PACKAGE

(57) **Abstract:** A method includes providing an article including an oxygen scavenger; forming the article into a container; placing an oxygen sensitive product into the container; and exposing the container to actinic radiation at a dosage effective to sterilize the container, and trigger the oxygen scavenger in the article. Alternative methods are also disclosed. A package includes a container, the container including an activated oxygen scavenger; wherein the container is sterilized; and wherein an oxygen sensitive product is disposed in the container.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 01/47870

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 B65B55/08 B65B55/19

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 B65B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)
EPO-Internal, PAJ, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 520 257 A (GRACE W R & CO) 30 December 1992 (1992-12-30) page 3, line 1 -page 3, line 41 page 6, line 23 -page 6, line 24	1-10
X	WO 98 05555 A (LUTHRA NARENDER P ;BOAL DILIP K (US); GRACE W R & CO (US); SPEER D) 12 February 1998 (1998-02-12) the whole document	1-10
X	US 3 670 874 A (BRUNNER ALFRED) 20 June 1972 (1972-06-20) column 2, line 60 -column 4, line 6	1-10
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

* & * document member of the same patent family

Date of the actual completion of the international search

16 July 2002

Date of mailing of the international search report

24/07/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl
Fax (+31-70) 340-3016

Authorized officer

Farizon, P

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 01/47870

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 1995, no. 10, 30 November 1995 (1995-11-30) & JP 07 186337 A (OKURA IND CO LTD), 25 July 1995 (1995-07-25) abstract ---	1-10
X	WO 95 33651 A (PHARMACIA AB ; AHLQVIST ANNA (SE); BERGLUND KJELL (SE); LUNDMARK ST) 14 December 1995 (1995-12-14) the whole document ---	1-10
X	WO 98 05571 A (MIRANDA NATHANAEL R ; CAREY MICHAEL J (US); GRACE W R & CO (US); CO) 12 February 1998 (1998-02-12) the whole document ---	1-10
X	US 5 834 079 A (MIRANDA NATHANAEL R ET AL) 10 November 1998 (1998-11-10) the whole document ---	1-10
X	US 5 904 960 A (BECRAFT MICHAEL L ET AL) 18 May 1999 (1999-05-18) the whole document -----	1-10

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/US 01/47870

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0520257	A	30-12-1992	US 5211875 A	18-05-1993
			AT 183533 T	15-09-1999
			AU 650140 B2	09-06-1994
			AU 1811192 A	07-01-1993
			AU 659773 B2	25-05-1995
			AU 5930594 A	16-06-1994
			BR 9202401 A	26-01-1993
			CA 2071079 A1	28-12-1992
			CZ 9201971 A3	13-01-1993
			DE 69229817 D1	23-09-1999
			DE 69229817 T2	25-05-2000
			DK 520257 T3	06-12-1999
			EP 0520257 A2	30-12-1992
			ES 2137936 T3	01-01-2000
			FI 922969 A	28-12-1992
			HU 66841 A2	30-01-1995
			IE 922117 A1	30-12-1992
			IL 102160 A	27-11-1995
			JP 5194949 A	03-08-1993
			MX 9203389 A1	01-12-1992
			NO 922537 A	28-12-1992
			NZ 243077 A	27-09-1993
			PL 175843 B1	26-02-1999
			PL 172392 B1	30-09-1997
			SK 197192 A3	07-09-1994
			RU 2093441 C1	20-10-1997
			US 5425896 A	20-06-1995
			US 5498364 A	12-03-1996
			ZA 9204349 A	24-02-1993
WO 9805555	A	12-02-1998	AU 734478 B2	14-06-2001
			AU 3969597 A	25-02-1998
			BR 9711017 A	28-09-1999
			CA 2262486 A1	12-02-1998
			EP 0921980 A2	16-06-1999
			JP 2000516560 T	12-12-2000
			NZ 333940 A	25-08-2000
			WO 9805555 A2	12-02-1998
US 3670874	A	20-06-1972	FR 2025430 A5	11-09-1970
			GB 1230950 A	05-05-1971
			NL 6900448 A	09-06-1970
JP 07186337	A	25-07-1995	NONE	
WO 9533651	A	14-12-1995	AU 690697 B2	30-04-1998
			AU 2688495 A	04-01-1996
			CA 2192365 A1	14-12-1995
			EP 0759873 A1	05-03-1997
			JP 10501204 T	03-02-1998
			WO 9533651 A1	14-12-1995
			US 5881534 A	16-03-1999
			ZA 9504735 A	26-01-1996
WO 9805571	A	12-02-1998	AT 213714 T	15-03-2002
			BR 9711006 A	17-08-1999
			CA 2262888 A1	12-02-1998
			DE 69710738 D1	04-04-2002

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 01/47870

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9805571	A		DK 921993 T3 EP 0921993 A1 JP 2000515466 T NZ 333943 A WO 9805571 A1	03-06-2002 16-06-1999 21-11-2000 25-08-2000 12-02-1998
US 5834079	A	10-11-1998	AU 727948 B2 AU 1988697 A BR 9708172 A CA 2247904 A1 CN 1218488 A DK 885257 T3 EP 0885257 A1 JP 2002504159 T NZ 331414 A US 2001008662 A1 WO 9732924 A1 US 6391403 B1 US 2002018865 A1 AT 204595 T DE 69706287 D1 DE 69706287 T2 EP 0952179 A2 ES 2162255 T3	04-01-2001 22-09-1997 27-07-1999 12-09-1997 02-06-1999 08-10-2001 23-12-1998 05-02-2002 28-04-2000 19-07-2001 12-09-1997 21-05-2002 14-02-2002 15-09-2001 27-09-2001 16-05-2002 27-10-1999 16-12-2001
US 5904960	A	18-05-1999	AT 218968 T AU 745214 B2 AU 1106499 A BR 9813157 A CA 2308058 A1 EP 1027207 A1 JP 2001520946 T WO 9921698 A1 US 6259107 B1	15-06-2002 14-03-2002 17-05-1999 15-08-2000 06-05-1999 16-08-2000 06-11-2001 06-05-1999 10-07-2001

THIS PAGE BLANK (USPTO)